

Cycology* Resin C4220
Americas: COMMERCIAL

PC+ABS Blend with 20% Glass Reinforce. High heat resistance; Excellent balance strength/rigidity; Good impact/appearance.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	940	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	940	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	2.6	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2.6	%	ASTM D 638
Tensile Modulus, 5 mm/min	65300	kgf/cm ²	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	1490	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	59000	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	46	cm-kgf/cm	ASTM D 4812
Izod Impact, unnotched, -30°C	49	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	8	cm-kgf/cm	ASTM D 256
Izod Impact, notched, -30°C	6	cm-kgf/cm	ASTM D 256
Instrumented Impact Total Energy, 23°C	218	cm-kgf	ASTM D 3763
Instrumented Impact Total Energy, -30°C	201	cm-kgf	ASTM D 3763
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	129	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	132	°C	ASTM D 648
PHYSICAL			
Specific Gravity	1.29	-	ASTM D 792
Melt Flow Rate, 260°C/5.0 kgf	16	g/10 min	ASTM D 1238

¹ Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume rate are measured on injection moulded samples. All samples are prepared according to ISO 294.

² Only typical data for material selection purpose. Not to be used for part or tool design.
³ This rating is not intended to reflect hazards presented this or any other material under actual fire conditions.
⁴ Own measurement according to UL.
⁵ Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由厂家发布, 我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！

SABIC
Innovative
Plastics™



Cycloloy* Resin C4220
Americas: COMMERCIAL

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由厂家发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！