

Cycolac* Resin CTR52
Asia Pacific: COMMERCIAL

Clear ABS. Vacuum cleaner and telephone parts.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	400	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	280	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	3.5	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	36	%	ASTM D 638
Tensile Modulus, 5 mm/min	19600	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	660	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	20300	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	9	cm-kgf/cm	ASTM D 256
Instrumented Impact Total Energy, 23°C	276	cm-kgf	ASTM D 3763
THERMAL			
Vicat Softening Temp, Rate B/50	97	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	83	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	72	°C	ASTM D 648
CTE, -40°C to 40°C, flow	1.06E-04	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	1.06E-04	1/°C	ASTM E 831
Relative Temp Index, Elec	50	°C	UL 746B
Relative Temp Index, Mech w/impact	50	°C	UL 746B
Relative Temp Index, Mech w/o impact	50	°C	UL 746B
PHYSICAL			
Specific Gravity	1.09	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.5 - 0.8	%	SABIC Method
Melt Flow Rate, 230°C/3.8 kgf	10	g/10 min	ASTM D 1238
OPTICAL			
Light Transmission, 2.54 mm	84	%	ASTM D 1003

¹ Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume rate are measured on injection moulded samples. All samples are prepared according to ISO 294.

² Only typical data for material selection purpose. Not to be used for part or tool design.
³ This rating is not intended to reflect hazards presented this or any other material under actual fire conditions.
⁴ Own measurement according to UL.
⁵ Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由厂家发布，我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！

Cycolac* Resin CTR52

Asia Pacific: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
ELECTRICAL			
Hot Wire Ignition {PLC}	4	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	1	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	0	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating (3)	1.49	mm	UL 94

¹ Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 230C/50% relative humidity. All properties, except the melt volume rate are measured on injection moulded samples. All samples are prepared according to ISO 294.

² Only typical data for material selection purpose. Not to be used for part or tool design.
³ This rating is not intended to reflect hazards presented this or any other material under actual fire conditions.
⁴ Own measurement according to UL.
⁵ Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由厂家发布, 我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！

Cycolac* Resin CTR52
Asia Pacific: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	UNIT
Injection Molding		
Drying Temperature	70 - 75	°C
Drying Time	2 - 4	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.01	%
Melt Temperature	205 - 245	°C
Nozzle Temperature	205 - 245	°C
Front - Zone 3 Temperature	215 - 240	°C
Middle - Zone 2 Temperature	205 - 225	°C
Rear - Zone 1 Temperature	195 - 215	°C
Mold Temperature	50 - 70	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	30 - 60	rpm
Shot to Cylinder Size	50 - 70	%
Vent Depth	0.038 - 0.051	mm

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity.
All properties, except the melt volume rate are measured on injection moulded samples.
All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.
3) This rating is not intended to reflect hazards presented this or any other material under actual fire conditions.
4) Own measurement according to UL.
5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由厂家发布, 我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！