

Elastollan® 670 A 10WU

Thermoplastic Polyurethane Elastomer (Polyester)

Elastogran GmbH

General		
Material Status	• Commercial: Active	
Availability	• Europe	
Additive	• Plasticizer	• UV Stabilizer
Forms	• Pellets	

Physical	Nominal Value	Unit	Test Method
Density	1.19	g/cm ³	ISO 1183

Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	35.0	MPa	ISO 527-2
Tensile Strain (Break)	650	%	ISO 527-2

Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	3.00	MPa	ISO 37
Tear Strength	40	kN/m	ISO 34-1

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	No Break		
23°C	No Break		

Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	70		ISO 868

Additional Information

Note: These properties were tested in accordance with the DIN test standard.
 Stress at 20% elongation, DIN 53504: 1 Mpa
 Abrasion Loss, DIN 53516: 40 mm³

Notes

¹ Typical properties: these are not to be construed as specifications.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由IDES发布, 我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！