

# Elastollan® LP 9212

## Thermoplastic Polyurethane Elastomer (Polyester)

Elastogran GmbH

General	
Material Status	• Commercial: Active
Availability	• Europe
Forms	• Pellets

Physical	Nominal Value	Unit	Test Method
Density	1.17	g/cm <sup>3</sup>	ISO 1183

Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	50.0	MPa	ISO 527-2
Tensile Strain (Break)	600	%	ISO 527-2

Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	5.00	MPa	ISO 37
Tear Strength	50	kN/m	ISO 34-1

Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	81		ISO 868

### Additional Information

Note: These properties were tested in accordance with the DIN test standard.  
Stress at 20% elongation, DIN 53504: 2 Mpa

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 [www.kedisujiao.com](http://www.kedisujiao.com)

备注：以上原料物性数据由IDES发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！