

Polystyrol 165 H

General Purpose Polystyrene

BASF Corporation

Product Description			
Polystyrol 165 H is a high molecular weight, good flowing grade, often blended with high impact extrusion grades.			
General			
Material Status	• Commercial: Active		
Availability	• Europe		
Features	• Food Contact Acceptable	• Good Flow	• High Molecular Weight
Uses	• Blending	• Sheet	
Agency Ratings	• BGVO Food Contact, Unspecified Rating	• FDA Food Contact, Unspecified Rating	
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	• Thermoforming
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (200°C/5.0 kg)	3.40	cm ³ /10min	ISO 1133
Water Absorption			ISO 62
Saturation, 23°C	< 0.10	%	
Equilibrium, 23°C, 50% RH	< 0.10	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	3300	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	52.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.0	%	ISO 527-2
Flexural Strength (23°C)	86.0	MPa	ISO 178
Shear Modulus (23°C)	1400	MPa	ISO 537
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	< 25	kJ/m ²	ISO 179/1eU
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	150	MPa	ISO 2039-1
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	84.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	76.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	97.0	°C	ISO 306/A120
--	89.0	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+14	ohms	IEC 60093
Volume Resistivity	> 1.0E+18	ohm·cm	IEC 60093
Relative Permittivity			IEC 60250
23°C, 100 Hz	2.50		
23°C, 1 MHz	2.50		
Electric Strength (23°C)	140	kV/mm	IEC 60243-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating - UL			UL 94
1.60 mm		HB	
3.20 mm		HB	
Injection	Nominal Value	Unit	
Processing (Melt) Temp	180 to 280	°C	
Mold Temperature	10.0 to 60.0	°C	
Extrusion Notes			
Flat Film Extrusion Melt Temperature: 200 to 240°C			

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由IDES发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！

Polystyrol 165 H
General Purpose Polystyrene
BASF Corporation

Saturday, December 26, 2009

Notes

¹ Typical properties: these are not to be construed as specifications.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由IDES发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！