

Terblend® N NG-06 (Cond)

Polyamide 6 + ABS

BASF Corporation

Product Description

Terblend N NG-06 is a 30% glass fiber reinforced ABS/PA6 blend with extra high rigidity and dimensional stability.

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber Reinforcement, 30% Filler by Weight
Features	• Good Dimensional Stability • High Rigidity
Agency Ratings	• ULC Unspecified Rating
RoHS Compliance	• RoHS Compliant
Forms	• Pellets
Processing Method	• Injection Molding

Mechanical	Nominal Value	Unit	Test Method
Tensile modulus	6500	MPa	ISO 527-2 ²
Tensile Stress (Break)	85.0	MPa	ISO 527-2 ²
Tensile Strain (Break)	3.5	%	ISO 527-2 ²
Flexural Modulus (23°C)	5500	MPa	ISO 178
Flexural Strength (23°C)	105	MPa	ISO 178

Notes

¹ Typical properties: these are not to be construed as specifications.

² Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由厂家发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！