

# Ultramid® B 32 01

Polyamide 6

BASF Corporation

## Product Description

Ultramid B32 01 is an intermediate viscosity, PA6 grade. It conforms to FDA requirements including, 21 CFR 177.1500, EU Directive 2002/72/EC, the German BfR recommendation "X Polyamide", 1.6.1998 or legislations for other countries will be provided on request.

## General

Material Status	• Commercial: Active		
Availability	• Europe	• North America	
Features	• Medium Viscosity	• Oil Resistant	
Uses	• Bi-axially Oriented Film	• Film	• Paper Coatings
Agency Ratings	• FDA 21 CFR 177.1500		
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Film Extrusion		

Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm <sup>3</sup>	ISO 1183
Apparent Density	0.70	g/cm <sup>3</sup>	ISO 60
Water Absorption			ISO 62 <sup>2</sup>
Saturation	9.5	%	
Equilibrium	2.6	%	
Viscosity Number (96% H <sub>2</sub> SO <sub>4</sub> )	184	cm <sup>3</sup> /g	ISO 307

Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC)	220	°C	ISO 3146

Additional Information	Nominal Value	Unit	Test Method
Moisture Content	< 0.10	%	ISO 15512
Pellet Shape	cylindrical		
Pellet Size	2.00 to 2.50	mm	
Relative Viscosity (1% in 96% Sulfuric Acid)	3.20		ISO 307

## Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 [www.kedisujiao.com](http://www.kedisujiao.com)

备注：以上原料物性数据由厂家发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！